

Butonal® NX 4190

Chemical Nature

Aqueous, high solids, cold-polymerized, cationic styrene-butadiene dispersion for modifying cationic asphalt emulsions

Properties

Typical Properties Solids content % ~ 64.0 pH ~ 5.4 Viscosity mPa s 250-2000

scosity mPa s 250 – 200 (Brookfield RV, Spindle #3, at 20 rpm)

Other Properties of the dispersion

Bound styrene % 24
Residual monomer % 0.08 max.
Antioxidant none
Glass transition temperature °C -53
(DSC)
Weight/volume lbs/gal ~ 8.17
Specific gravity ~ 0.98

Application

Features

Butonal NX 4190 is a mechanically stable latex polymer dispersion that is readily incorporated into cationic asphalt emulsions through addition to the soap solution (batch process) or co-milling (continuous process). Butonal NX 4190 provides excellent cohesion and adhesion properties with aggregate and significantly enhances the residue properties such as Forced Ductility, Toughness & Tenacity, Torsional Recovery and Softening Point over conventional cationic polymers.

Applications

Butonal NX 4190 is used in the following applications:

- Chip Seal
- Slurry seal
- Microsurfacing

Butonal NX 4190 can also be used to modify hot asphalt cements in order to meet Superpave[®] "Plus" modified binder specifications as well as to provide improvements in conventional properties such as increased softening point and decreased penetration.

Processing

Periodic mechanical stirring is required to maintain a homogeneous mixture. Some separation is possible due to the specific gravity and particle size distribution of this latex polymer dispersion.

Generally, the preferred means of stirring is with a separate propeller type stirrer. This low-speed, low-shear mechanical stirrer can be located off-center, set at an angle, or side-mounted near the tank bottom to prevent latex foaming or vortex formation. Center-stirring requires tank baffles. It is recommended that material be agitated for 10 - 20 minutes every 24 hours in storage.

^{*} The above values should not be taken as specification.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Butonal NX 4190

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Butonal is a registered trademark of BASF Group.

© BASF Corporation, 2020



BASF Corporation is fully committed to the Responsible Care[®] initiative in the USA, Canada, and Mexico. For more information on Responsible Care[®] go to: U.S.: www.basf.us/responsiblecare_usa Canada: www.basf.us/responsiblecare canada

Canada: www.basf.us/responsiblecare_canada México: www.basf.us/responsiblecare_mexico

BASF Corporation Dispersions and Resins 11501 Steele Creek Road Charlotte, North Carolina 28273 Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com Email: edtech-info@basf.com www.basf.us/formulation-additives