

Joncryl[®] HPB 4030

Product Description	Joncryl HPB 4030 is a water resistant, heat sealable binder for replacing extruded wax or polyethylene coatings on paper substrates for cups, boxes, and other types of food packaging.
Key Features & Benefits	<ul style="list-style-type: none">- Excellent water resistance- Heat sealable- Good hot tack (bond strength at high use temperature)- Low odor
Chemical Composition	RC acrylic emulsion

Properties

Typical Characteristics	Appearance		translucent emulsion
	Non-volatile	%	40.0
	pH		7.5
	Acid number (NV)		28
	Viscosity at 25°C (Brookfield #2 LV spindle, 30 rpm)	cps	100
	Density at 25°C	g/cm ³	1.08
	MFFT	°C	<5
	Freeze-thaw stable		No

Applications

Joncryl HPB 4030 is a film forming, heat sealable, water resistant emulsion designed for applications where poly-coated board is currently used. Due to its good bond strength at high use temperatures, it is particularly suited for hot cups.

Performance is strongly dependent on dry film thickness; gravure or rod coating application works best.

Joncryl HPB 4030 is recommended for applications such as:

- Hot and cold cups
- Boxes, trays and other food packaging and food service items

Starting Point Formulation

The following starting point formulations are recommended for initial evaluations of Joncryl HPB 4030. Further optimization of the formulations will be required to achieve desired results for specific applications. End use performance will be dependent on dry coat weight.

For end uses requiring excellent water resistance (20-minute Cobb < 2.0 g/m²) and good bond strength at elevated temperatures:

1st layer	
Joncryl HPB 4010	99.7%
Sterocoll FS na	0.2%
Defoamer	0.1%
Water	As needed for application viscosity
Target dry coating weight: 8 gsm	

2nd layer	
Joncryl HPB 4030	89.4%
Joncryl DFC 3050	10.0%
Sterocoll FS na	0.5%
Defoamer	0.1%
Water	As needed for application viscosity
Target dry coating weight: 5 gsm	

For single layer application:

One layer	
Joncryl HPB 4030	89.4%
Joncryl DFC 3050	10%
Sterocoll FS na	0.5%
Defoamer	0.1%
Water	As needed for application viscosity
Target dry coating weight: 15 gsm, or as needed	
(lower coat weight → higher Cobb value)	

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care practices, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl HPB 4030.

Storage

Please refer to the "Handling and Storage of Polymer Dispersion" brochure

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

Joncryl and Sterocoll are registered trademarks of BASF Group.

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care, go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions