

Dispex[®] Ultra FA 4480

general

- low molecular weight wetting and dispersing agent with excellent pigment wetting properties
- especially suitable for coatings and aqueous pigment pastes

chemical nature

solution of modified fatty alcohol polyglycoether in water

Properties

physical form

viscous liquid

storage

Dispex[®] Ultra FA 4480 should be stored in tightly closed containers and in a cool place. The packed product is not damaged by low temperatures or by frost. If stored below 10°C precipitation or gelatinization of the product is possible. This process is reversible.

typical properties

solvent	water
cloud point	~ 63 °C
water content	~ 20%
pH value	~ 6.5

Application

Dispex[®] Ultra FA 4480 shows excellent wetting and dispersing properties in aqueous, binder and solvent-free pigment pastes. It provides outstanding flow properties even at high pigment load.

Dispex[®] Ultra FA 4480 improves pigment wetting and therefore also increases gloss and color intensity of the paint, especially in combination with organic pigments. Dispex[®] Ultra FA 4480 shows excellent results in waterbased alkyds, polyester resins and also in aqueous polyurethane emulsions.

recommended concentrations

the dosage used in pigment pastes strongly depends on the actual pigments. Typical addition levels for pigment pastes, calculated on the weight of pigment are as follows:

inorganic pigments	1 - 5%
organic pigments	10 - 30%
carbon black	up to 50%

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Dispex Ultra FA 4480; Dispex Ultra FA 4480, Dispex Ultra FA 4480 NU.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

[®] = registered trademark, [™] = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives